



FX 90 FUSING PRODUCTS

PHYSICAL PROPERTIES

The physical properties of glass vary slightly from color to color. Use these measured points as 'typical' or an average over the FX 90 colors made by Uroboros.

TYPICAL ANNEALING POINTS:

Transparents: 977° F (525° C)

Opals: 955° F (512° C)

TYPICAL STRAIN POINTS:

Transparents: 910° F (488° C)

Opals: 875° F (468° C)

TYPICAL SPECIFIC GRAVITY:

2.5 – 2.6 grams per cubic centimeter

156 – 162 lb per cubic foot

ART GLASS

FX 90

SYSTEM 96®