



## SYSTEM 96 FUSING PRODUCTS

### PHYSICAL PROPERTIES

The physical properties of glass vary slightly from color to color. Use these measured points as 'typical' or an average over the System 96 colors made by Uroboros.

**TYPICAL ANNEALING POINTS:**

Transparents: 965° F (517° C)

Opals: 935° F (501° C)

**TYPICAL STRAIN POINTS:**

Transparents: 900° F (481° C)

Opals: 860° F (457° C)

**TYPICAL SPECIFIC GRAVITY:**

2.5 – 2.6 grams per cubic centimeter

156 – 162 lb per cubic foot

ART GLASS

FX 90

SYSTEM 96®